

# OK Tigrod 316L GTAW ER316L

## Description

Bare, corrosion-resistant, chromium-nickel-molybdenum rods for welding austenitic stainless alloys of the 18% Cr-8% Ni and 18% Cr-10% Ni-3% Mo types.

OK Tigrod 316L has good general corrosion resistance, particularly to corrosion in acid and chlorinated environments. The alloy has a low carbon content which makes it particularly recommended when there is a risk of intergranular corrosion. The alloy is widely used in the chemical and food-processing industries, as well as in shipbuilding and various types of architectural structure.

## Welding current

DC(-)

## Classifications

SFA/AWS A5.9	ER316L
EN 12072	W 19 12 3 L
Werkstoffnummer	~1.4430

## Wire composition

C	Si	Mn	Cr	Ni	Mo	Cu
<0.03	0.5	1.8	19.0	12.5	2.8	<0.3

## Typical mech. properties all weld metal

Yield stress, MPa	470
Tensile strength, MPa	650
Elongation, %	32

## Charpy V

Test temps, °C	Impact values, J
+20	140
-60	110
-196	70

## Approvals

CL	
DNV	316L (-60°C)
Sepros	UNA 485179
UDT	DIN 8556
VdTÜV	

## Packing data

Diameter, mm	Length, mm	Weight of rods/ box, kg
1.0	1000	5.0
1.2	1000	5.0
1.6	1000	5.0
2.0	1000	5.0
2.4	1000	5.0
3.2	1000	5.0
4.0	1000	5.0

This document was created with Win2PDF available at <http://www.win2pdf.com>.  
The unregistered version of Win2PDF is for evaluation or non-commercial use only.  
This page will not be added after purchasing Win2PDF.